




Inox

Stainless, acid- and heat-resistant steels



Quality	Designation	International Designation	
1.3912	Ni36	UNS K93603	
1.3974	X2CrNiMnMoNNb23-17-6-3	UNS S33228	
1.3964	X2CrNiMnMoNNb21-13-5-3	XM-19	
1.4003	X2CrNi12 / X2Cr11	UNS S40977	
1.4005	X12CrS13	416	
1.4006	X12Cr13	410	UNS S41000
1.4016	X6Cr17	430	UNS S43000
1.4021	X20Cr13	420	UNS S42000
1.4028	X30Cr13	420	UNS S42020
1.4034	X46Cr13	420	
1.4037	X65Cr13		
1.4057	X17CrNi16-2	431	
1.4104	X14CrMoS17	430F	
1.4111	X110CrMoV15		
1.4112	X90CrMoV18	440B	
1.4116	X50CrMoV15		

Excerpt from our common materials.
Further materials on demand.

Walzwerke Einsal GmbH
Altener Straße 85
58769 Nachrodt


Tel.: +49 2352 332-233

Fax: +49 2352 332-192
E-Mail: info@einsal.com



Inox

Stainless, acid- and heat-resistant steels



Quality	Designation	International Designation	
1.4122	X39CrMo17-1		
1.4125	X105CrMo17	440C	
1.4162	X2CrMnNiN22-5-2		UNS S32101
1.4301	X5CrNi18-10	304	UNS S30400
1.4303	X4CrNi18-12	305 / 308	
1.4305	X8CrNiS18-9	303	
1.4306	X2CrNi19-11	304L	
1.4307	X2CrNi18-9	304L	
1.4310	X10CrNi18-8	301	
1.4313	X3CrNiMo13-4	F6NM	UNS S41500
1.4362	X2CrNiN23-4	2304	UNS S32304
1.4404	X2CrNiMo17-12-2 / X2CrNiMo17-13-2	316L	UNS S31603
1.4410	X2CrNiMoN25-7-4	F53	UNS S32750
1.4418	X4CrNiMo16-5-1		
1.4432	X2CrNiMo17-12-3	316L	UNS S31603
1.4435	X2CrNiMo18-14-3	316L	UNS S603

Excerpt from our common materials.
Further materials on demand.

Walzwerke Einsal GmbH
Altener Straße 85
58769 Nachrodt


Tel.: +49 2352 332-233

Fax: +49 2352 332-192
E-Mail: info@einsal.com



Inox

Stainless, acid- and heat-resistant steels



Quality	Designation	International Designation	
1.4441	X2CrNiMo18-15-3	316LVM	
1.4462	X2CrNiMoN22-5-3	F51	UNS S31803
1.4472	X4CrNiMnMo21-9-4	F1586	UNS S31675
1.4501	X2CrNiMoCuWN25-7-4	F55	UNS S32760
1.4529	X1NiCrMoCuN25-20-7		UNS N02986
1.4534	X3CrNiMoAl13-8-2	XM-13	UNS S13800
1.4539	X1NiCrMoCu25-20-5	904L	UNS S08904
1.4541	X6CrNiTi18-10	321	
1.4542	X5CrNiCuNb16-4	630	UNS S17400
1.4545	X5CrNiCuNb15-5-5	XM-12	UNS S15500
1.4548	X5CrNiCuNb17-4-4	630	UNS S17400
1.4550	X6CrNiNb18-10	347 / 348	
1.4568	X7CrNiAl17-7	631	
1.4571	X6CrNiMoTi17-12-2	316Ti	
1.4597	X8CrMnCuNi17-8-3	204Cu	
1.4713	X10CrAlSi7 / X10CrAl7		

Excerpt from our common materials.
Further materials on demand.

Walzwerke Einsal GmbH
Altener Straße 85
58769 Nachrodt


Tel.: +49 2352 332-233

Fax: +49 2352 332-192
E-Mail: info@einsal.com



Inox

Stainless, acid- and heat-resistant steels



Quality	Designation	International Designation	
1.4742	X10CrAlSi18 / X10CrAl18	442	
1.4762	X10CrAlSi25	AISI 446	UNS S44600
1.4828	X15CrNiSi20-12	309	
1.4841	X15CrNiSi25-21 / X15CrNiSi25-20	310 / 314	
1.4845	X8CrNi25-21 / X12CrNi25-21	310S	
1.4878	X8CrNiTi18-10 / X12CrNiTi18-9	321H	
1.4903	X10CrMoVNb9-1	A213	UNS S50460
1.4913	X19CrMoNbVN11-1		
1.4923	X22CrMoV12-1 / X21CrMoNiV12-1		
1.4938	X12CrNiMoV12-3		UNS S64152
1.4939	X12CrNiMo12 / X12CrNiMoN12		UNS S64152
1.4980	X6NiCrTiMoVB25-15-2	606	UNS S66286

Excerpt from our common materials.
Further materials on demand.

Walzwerke Einsal GmbH
Altener Straße 85
58769 Nachrodt

Tel.: +49 2352 332-233

Fax: +49 2352 332-192
E-Mail: info@einsal.com